

---

## Synthite AC-41 Polyurethane varnish

Synthite AC-41 is an air drying finishing varnishes based on polyurethane.

---

### Attributes

Synthite AC-41 has the following excellent properties:

- fast drying - units can be handled in 30 min.
- easy application (dipping, brushing, spraying)
- hohe Temperaturbeständigkeit
- superior abrasion resistance
- excellent adhesion to most surfaces
- transformer oil resistance ASTM D 155-55
- corrosion and humidity resistance

---

### Application

Typical application areas are:

- Stators
- Rotors
- Transformers
- Resistors
- Capacitors

---

### Standards

Class H (180 °C) acc. UL 1446, MW 35-C, Twisted Pairs.

---

### Delivery forms

4.5 kg, 22.5 kg and spray bottles on request.

---

### Base

Clear

---

### Color

Clear

---

### Storage

Store in cool dry place (max. 30 °C) away from direct sunlight. Protect from moisture and humidity. Shelf life is 36 months when stored in closed original container at max. 30 °C.

---

---

## Hardening

Curing is possible in explosion protected environments under a fume hood at ambient conditions:

Air drying times at 25 °C:

- 10 min. dust-dry
- 1 h touch-proof
- 48 h cured

---

## Protection

Cured Synthite AC-41 is biologically inactive and safe to health. Always refer to the safety data sheet and implement common protective measures when processing the varnish.

---

## Processing

When spray-coating with thinner T 200, Synthite AC-41 is adapted to processing viscosities in common manual spraying nozzles. Usually you 20-25 % thinner. It is possible to adjust the viscosity with T200 for dip coating. Before longer air contact, ensure that the dipping bath surface does not become dry by placing a nitrogen blanket. Synthite AC-41 is supplied ready-to-use for brushing application. Recommended coating thickness: less than 30-40 µm. Always observe the specifications on the safety data sheet and relevant safety organisation regulations.

---

## Cleaning

Clean tools with thinner T 200 in time. Maintenance and care of coating equipment, especially cleaning, must be carried out according to operational requirements. Always refer to the user manual of the equipment.

Mechanical	Unit of measure	Conditions	Value	Test method
Coating thickness	µm		60-75	ASTM D-115

Electrical	Unit of measure	Conditions	Value	Test method
Dielectric strength	kV/mm	dry / 0.025 mm film thickness	80	
Dielectric strength *	kV/mm	after 24 h water immersion / 0.025 film thickness	48	ASTM D-115

Chemical	Conditions	Blistering	Rusting	Cracking	Test method
Resistance	Water	no	no	no	ISO 4628/2-3-4
Resistance	1% Natrium hydroxide	no	no	no	ISO 4628/2-3-4
Resistance	saltwater	no	no	no	ISO 4628/2-3-4
Resistance	10 % sulfuric acid	no	no	no	
Resistance	no				

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 04/24



Liquid phase	Unit of measure	Conditions
Dilution		
Viscosity	s	25 °C
Specific density	g/cm <sup>3</sup>	25 °C
Viscosity	s	25 °C

Liquid phase	Unit of measure	Values	Test method
Dilution		4:1	
Viscosity	s	50-65	Ford Cup 4
Specific density	g/cm <sup>3</sup>	0.88-0.92	
Viscosity	s	40-60	ISO Cup 6

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 04/24

