Synthite EB-43/387-D Polyester enamel varnish Page 1 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



# Synthite EB-43/387-D Polyester enamel varnish

Synthite EB-43/387-D is a black, very quick drying Polyester enamel varnish.

### **Attributes**

Synthite EB- 43/387-D has the following excellent properties:

- very fast drying
- UL-approved
- excellent chemical resistance
- oil and moisture resistant
- hard, smooth, abrasion resistant film
- good adhesion
- good electrical properties
- transformer oil resistance ASTM D 155-55
- corrosion and humidity resistance

# **Application**

Typical applications for Synthite EB-43/387-D are:

- stators
- printed circuit boards
- · form wound coils
- resistors
- transformers
- bus bars

### **Standards**

class H (180°C) UL 1446

UL-file-no. OBOR2.E317427 and OBJS2.E317429

| magnet wire | Twisted Pairs | Helical Coil |
|-------------|---------------|--------------|
| MW 24-C     | 155 °C        | 155 °C       |
| MW 28-C     | 130 °C        | 130 °C       |
| MW 35-C     | 180 °C        | 180 °C       |







#### **Product datasheet**

Synthite EB-43/387-D Polyester enamel varnish Page 2 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| _   |       | •     |
|-----|-------|-------|
| Dei | iverv | forms |

5 kg, 25 kg and spray cans on request.

### Storage

Store in cool, dry place (max. 30 °C) away from direct sunlight. Proect from moisture and humidity. Shelf-life is 24 months when stored in closed original containers at max. 30 °C.

# Hardening

Air-drying tim (on copper plate):

60 min. - set to touch

### **Protection**

Use in well ventilated areas, avoid contact with scin and eyes and wear protective clothes. For more details see the safety data sheet.

### **Processing**

Updated 04/24

For spraying application, Synthite EB-43/387-D must be thinned with 15 % of Dolph's® T-200 thinner. It is supplied with a viscosity suitable for application by brush.







#### **Product datasheet**

Synthite EB-43/387-D Polyester enamel varnish Page 3 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| Mechanical        | Unit of<br>measure | Conditions | Values | Test method   |
|-------------------|--------------------|------------|--------|---------------|
| Coating thickness | μm                 |            | 75-100 | ASTM D-115-55 |

| Electrical          | Unit of<br>measure | Conditions  | Value | Test method   |
|---------------------|--------------------|---|-------|---------------|
| Dielectric strength | kV/mm              | dry / 0.025 mm film<br>thickness                          | 80    | ASTM D-115    |
| Dielectric strength | kV/mm              | after 24 h water<br>disposal / 0.025 mm<br>film thickness | 48    | ASTM D-115    |
| Creep resistance    |                    |   | 600 M | DIN IEC 60112 |

| Chemical   | Conditions<br>ISO 2812-2 /<br>168 h | Blistering | Rusting | Cracking | Test method       |
|------------|-------------------------------------|------------|---------|----------|-------------------|
| Resistance | Water                               | no         | no      | no       | ISO<br>4628/2-3-4 |
| Resistance | 10 %<br>sulphuric<br>acid           | no         | no      | no       | ISO<br>4628/2-3-4 |
| Resistance | 1 % Sodium<br>hydroxide             | no         | no      | no       | ISO<br>4628/2-3-4 |
| Resistance | Salt water                          | no         | no      | no       | ISO<br>4628/2-3-4 |

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 04/24







#### **Product datasheet**

Synthite EB-43/387-D Polyester enamel varnish Page 4 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| Liquid phase     | Unit of measure | Conditions |
|------------------|-----------------|------------|
| Viscosity        | S               | 25 °C      |
| Viscosity        | S               | 25 °C      |
| Specific density | g/cm³           | 25 °C      |

| Liquid phase     | Unit of measure | Values    | Test method |
|------------------|-----------------|-----------|-------------|
| Viscosity        | S               | 60-80     | Ford Cup 4  |
| Viscosity        | S               | 75-100    | ISO Cup 5   |
| Specific density | g/cm³           | 1.07-1.13 |             |





