
Voltatex® 4130 1-component-resin

Voltatex® 4130 is a cloudy, yellow-brown, vinyl toluene based, styrene-free single-component impregnating resin that is ready to use, based on unsaturated polyesterimide resins.

Attributes

- single component
- very high capillary activity
- low evaporation losses while processing
- high resin retention in the object
- low draining losses in the oven

The cured resin compound is characterized by:

- high thermal endurance
- excellent bond strength
- high thermal and mechanical stability, especially under extreme long term stress
- tough and hard resin compound

Application

- stators
- transformers
- suitable for: Insulation systems of thermal class 180 (H)

Standards

- UL-File-Nr.: E 101752 (M) Underwriters Laboratories Inc., USA
- Isolation-system temperature of thermal class 180 (H) acc. to IEC 60085:2007
- Temperature Index in acc. with IEC 60455-3-5, Type 180, Testing Method in acc. with IEC 60216
- Polybromited diphenylether 2003/11/EU (PBDE)
- Temperature class acc. to UL 1446:

Twisted Pair ASTM D2307 MW 30:200
MW 35:180

Helical Coil ASTM D2519 MW 30:200

Insulation-system acc. to UL 1446 (IEC 61858):

Class 130 C190HE

R150HE

Z130HE

Z150HE

Class 155 C290HE

CZ255HE

R201HE

R203HE

Z200HE

Class 180 R342HE

Delivery forms

Voltatex® 4130 is supplied in one-way-cans containing 25 kg.

Storage

In closed original cans the resin can be stored for 6 months if provided storage temperature does not exceed 25 °C.

Hardening

In order to minimize evaporation of reactive components while curing the impregnated objects should be heated up to the curing temperature in the shortest possible time. The air flow in the curing oven should be kept to the minimum permitted by safety considerations.

Curing time:

at 130 °C: 3h

at 150 °C: 1h

Protection

Cured Voltatex® 4130 is biologically inactive and not dangerous to health. When processing the liquid resin please refer to the Material Safety Data Sheet (MSDS) for Voltatex® 4130 and the regulations of your local authority.

Processing

The impregnating resin can be applied by using

- all kind of conventional dip & bake equipment

-
- continuous and vacuum dip processes
 - VPI process

Unlimited tank stability can be achieved as long as Voltatex® 4130 is kept below 25 °C and at least 30 % of the tank content is used and replaced with fresh resin per month. For optimum process viscosity it is possible to add Voltatex® T032.

Cleaning

Once cured Voltatex® 4130 is almost insoluble. Therefore, application equipment should be cleaned regularly with cleaner Voltatex® T050.

All equipment cleaning and maintenance should be carried out in accordance with the equipment manufacturer's instructions.

Mechanical	Unit of measure	Conditions	Values	Testing method
Bond strength of twisted coils	N	Room temperature	230 ± 20	IEC 60455-2, test method A acc. IEC 61033
Bond strength of twisted coils 130 °C	N	130 °C	33 ± 8	IEC 60455-2, test method A acc. IEC 61033
Bond strength of twisted coils 155 °C	N	155 °C	30 ± 5	IEC 60455-2, test method A acc. IEC 61033
Bond strength of twisted coils 180 °C	N	180 °C	30 ± 5	IEC 60455-2, test method A acc. IEC 61033
Shore-D-hardness		room temperature	50 ± 5	acc. IEC 60455-2, ISO 868

Thermal	Unit of measure	Conditions	Values	Testing method
Temperature index	°C	IEC 60455-3-5	180	acc. IEC 60216
Testing voltage IEC 60317-13	°C	MW 35	196	IEC 60172
Testing voltage IEC 60317-8	°C	MW 30	209	IEC 60172
Bond strength IEC 60317-13	°C	IEC 61033 / MW 35	214	method B, final point 22 N

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 04/24

Voltatex® is a registered trademark of Axalta Coating Systems LLC., Philadelphia PA 19103, USA.



Thermal	Unit of measure	Conditions	Values	Testing method
Thermal conductivity	$W(m \cdot K)^{-1}$		0.17	acc. DIN 501046

Chemical	Conditions	Values	Testing method
Resistance	Hexane	resistant	Energy Solutions, Voltatex® 019
Resistance	Transformer oil, distilled water, 5 % soap-flock-dilution	resistant	acc. Axalta company standard

Electrical	Unit of measure	Conditions	Values	Testing method
Dielectric strength at 23 °C and 50 % r.h.	kV/mm	typ. value	74	IEC 60455-2 test method acc. IEC 60243-1
Dielectric strength at 155 °C	kV/mm	typ. value	72	IEC 60455-2, test method acc. IEC 60243-1
Dielectric strength at 23 °C after 96 h storage at 92 % r.h.	kV/mm	typ. value	90	IEC 60455-2 test method acc. IEC 60243-1
Dielectric strength at 105 °C after 168 h oil immersion	kV/mm	typ. value	130	IEC 60455-2 test method acc. IEC 60243-1
Specific volume resistance at 155 °C	$\Omega \cdot cm$	typ. value	5×10^{10}	IEC 60455-2 test method acc. IEC 60093

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 04/24

Voltatex® is a registered trademark of Axalta Coating Systems LLC., Philadelphia PA 19103, USA.



Electrical	Unit of measure	Conditions	Values	Testing method
Specific volume resistance at 180 °C	$\Omega \cdot \text{cm}$	typ. value	1×10^{10}	IEC 60455-2 test method acc. IEC 60093
Specific volume resistance after 7 d water immersion	$\Omega \cdot \text{cm}$	typ. value	8×10^{15}	IEC 60455-2 test method acc. IEC 60093
Creep resistance		typ. value	CTI 600 M	IEC 60455-2, test method acc. IEC 60234-1
Dielectric constant at 23 °C between 50 Hz and 1 MHz			3.4 ± 0.5	IEC 60455-2 test method acc. IEC 60250
Loss factor at 155 °C and 50 Hz			100×10^{-3} - 300×10^{-3}	IEC 60455-2 test method acc. IEC 60250
Loss factor cross section $0.2 = 200 \times 10^{-3}$	°C		145-170	IEC 60455-2 test method acc. IEC 60250

Liquid phase	Unit of measure	Conditions	Values	Testing method
Flow time	s	23 °C	75 ± 10	acc. DIN 53211
Reaction process gel time	min	typ. value	7.7	100 °C, company standard Voltatex® 014
Reaction process reaction time	min	typ. value	12.9	100 °C, company standard Voltatex® 014
Viscosity	mPas	25°C	265 ± 30	acc. DIN 53019

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 04/24

Voltatex® is a registered trademark of Axalta Coating Systems LLC., Philadelphia PA 19103, USA.



Liquid phase	Unit of measure	Conditions	Values	Testing method
VOC acc. 31. BLmSchV		typ. value	approx. 5.2 %	mass

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 04/24

Voltatex® is a registered trademark of Axalta Coating Systems LLC., Philadelphia PA 19103, USA.

