
SynKraft® VSP H2

SynKraft® VSP H2 is a tear-proof, flexible 2-ply insulation consisting of a polyester film with special presspaper attached to one side.

Attributes

The pressboard displays good absorption of impregnants, resulting in exceptional bonding between all winding components after impregnating.

The polyester film improves the electrical and mechanical properties of the pressboard layer in the composite material, especially the resistance to tears, and provides excellent gliding properties for an automatic winding feed. On the other hand, the pressboard layer facing the laminated core is protected by the polyester film during processing.

Application

SynKraft® VSP H2 is used as an extremely costeffective slot insulation and slot closure in stators and rotors, especially for small motors, and is often applied as interlayer insulation and final insulation in small transformers.

Standards

- Class B (130 °C) insulating material
- Insulation according to IEC 60626
- Test method IEC 60641-2
- Sample conditioning acc. to standard atmosphere 23/50

Delivery forms

Total thickness in µm:

100, 130, 180, 230, 280, 330, 380

SynKraft® VSP H2 can be supplied as:

- in slit rolls from widths of 6 mm (depending on thickness) and above
- in rolls approx. 630 mm or 1,260 mm
- in sheets approx. 630 mm x 800 mm or approx. 800 mm x 1,260 mm

Feathering:

- depth approx. 1 - 12 mm, distance approx. 1 - 10 mm
- from widths of 10 to 240 mm and thickness of 0.20 mm

Base

PET-film + one-sided special pressboard overlay

Mechanical	Unit of measure						
Total thickness	mm	0.10	0.13	0.18	0.23	0.28	0.33
Nominal thickness of film	µm	23	23	23	23	23	23
Specific weight	g/m ²	115	165	215	290	350	430
Elongation at break longitudinal	%	3	3	3	5	5	5
Elongation at break transversal	%	10	10	10	13	13	13
Tensile strength longitudinal	N/mm ²	100	85	90	90	90	85
Tensile strength transversal	N/mm ²	65	60	60	60	60	60

Mechanical	Unit of measure	
Total thickness	mm	0.38
Nominal thickness of film	µm	23
Specific weight	g/m ²	500
Elongation at break longitudinal	%	5

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 10/18

SynKraft® is a registered trademark of SynFlex.



Mechanical	Unit of measure	
Elongation at break transversal	%	13
Tensile strength longitudinal	N/mm ²	90
Tensile strength transversal	N/mm ²	60

Electrical	Unit of measure						
Total thickness	mm	0.10	0.13	0.18	0.23	0.28	0.33
Dielectric strength	kV	7	7	7	8	8	9

Electrical	Unit of measure	
Total thickness	mm	0.38
Dielectric strength	kV	9

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 10/18

SynKraft® is a registered trademark of SynFlex.

