
SynTherm® P

SynTherm® P is a flexible polyester film based on polyethylene terephthalate. With increasing thickness the film appears to be cloudy or milky white.

Attributes

With its excellent balance of electrical properties SynTherm® P offers many constructional possibilities for the electrical industry. It is suitable for use in a temperature range from -40 °C to +140 °C short-term.

Application

Polyester film SynTherm® P is suitable for systems up to 130 °C. It is used in motor and generator engineering as wedge and for slot insulation or phase insulation. In transformers, chokes and relays it is often used as core, layer or final insulation.

Delivery forms

Film thickness in µm:

23, 36, 50, 75, 100, 125, 190, 250, 300, 350

(further thicknesses on request)

SynTherm® P is available:

- tapes as of 6 mm width
- rolls up to 1,000 mm width

Feathering:

- depth approx. 1 - 12 mm, distance approx. 1 - 10 mm
- as of 10 mm up to 240 mm width of tape,

material thickness on request

Base

PET

| Mechanical | Unit of measure | | | | | | |
|---|-------------------|------|------|-----|-----|-----|-----|
| Total thickness | µm | 23 | 36 | 50 | 75 | 100 | 125 |
| Specific weight | g/m ² | 32.2 | 50.4 | 70 | 105 | 140 | 175 |
| Tensile strength longitudinal | N/mm ² | 196 | 196 | 186 | 186 | 176 | 176 |
| Tensile strength transversal | N/mm ² | 196 | 196 | 186 | 186 | 176 | 176 |
| Elongation at break longitudinal | % | 130 | 130 | 140 | 140 | 140 | 140 |
| Elongation at break transversal | % | 120 | 120 | 130 | 130 | 130 | 130 |
| Shrinkage (30 min at 150 °C) longitudinal | % | 1.8 | 1.6 | 1.6 | 1.4 | 1.2 | 1.2 |
| Shrinkage (30 min at 150 °C) transversal | % | 0.4 | 0.4 | 0.4 | 0.4 | 0.4 | 0.4 |

| Mechanical | Unit of measure | | | | |
|-------------------------------|-------------------|-----|-----|-----|-----|
| Total thickness | µm | 190 | 250 | 300 | 350 |
| Specific weight | g/m ² | 266 | 350 | 420 | 490 |
| Tensile strength longitudinal | N/mm ² | 176 | 176 | 166 | 166 |

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 07/21

SynTherm® is a registered trademark of SynFlex.



| Mechanical | Unit of measure | | | | |
|---|-------------------|-----|-----|-----|-----|
| Tensile strength transversal | N/mm ² | 176 | 176 | 166 | 166 |
| Elongation at break longitudinal | % | 150 | 150 | 150 | 150 |
| Elongation at break transversal | % | 140 | 140 | 140 | 140 |
| Shrinkage (30 min at 150 °C) longitudinal | % | 1.2 | 1.2 | 1.2 | 1.2 |
| Shrinkage (30 min at 150 °C) transversal | % | 0.4 | 0.4 | 0.4 | 0.4 |

| Electrical | Unit of measure | | | | | | |
|---------------------|-----------------|-----|-----|-----|------|-----|-----|
| Total thickness | µm | 23 | 36 | 50 | 75 | 100 | 125 |
| Dielectric strength | kV | 4.5 | 7.5 | 9.5 | 12.5 | 14 | 17 |

| Electrical | Unit of measure | | | | |
|---------------------|-----------------|-----|-----|-----|-----|
| Total thickness | µm | 190 | 250 | 300 | 350 |
| Dielectric strength | kV | 20 | 22 | 24 | 26 |

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 07/21

SynTherm® is a registered trademark of SynFlex.

