
Teonex® Q5100

Teonex® Q5100 is a flexible, slightly cloudy, biaxially oriented polyethylenenaphthalate (PEN) film.

Attributes

Compared to PET polyester film, Teonex® Q5100 has optimum properties in every respect.

The increased temperature resistance results in film approval in thermal class F (155 °C). It has a electrical relative temperature index (RTI) of 180 °C and a mechanical RTI of 160 °C according to UL.

Further advantages of Teonex® Q5100 are:

- extremely high dielectric strength
- very good mechanical strength
- high-level of stiffnes
- low water absorption
- easy to laminate

Application

Teonex® Q5100 was specially developed for use in electric motors with increased load as slot insulation, phase insulation and wedges.

Standards

- Class F (155 °C) insulating material
- UL approved, file no. E51743

Delivery forms

Film thicknesses in µm:

- from 12, 16, 25, 38, 50, 75,100, 125, 188, 250

Teonex® Q5100 can be supplied:

- in slit rolls from widths of 6 mm (depending on thickness) and above.
- in rolls up to a width of 1,000 mm

Overall diameter of the slit rolls/ rolls

- approx. 240, 330 or 450 mm.

Feathering:

- depth approx. 1 - 12 mm, distance approx. 1 - 10 mm
- from widths of 10 to 240 mm and thickness of 0.125 mm

Base

Polyethylenaphthalte

Mechanical	Unit of measure						
Nominal thickness	µm	12	16	25	38	50	75
Tensile strength longitudinal	MPa	305	319	314	263	269	262
Tensile strength transversal	MPa	306	334	320	254	284	261
Elongation at break longitudinal	%	82	79	75	113	89	84
Elongation at break transversal	%	82	91	88	89	95	93
Shrinkage (30 min at 150 °C) longitudinal	%	0.1	0.2	0.1	0.6	0,0	0.3
Shrinkage (30 min at 150 °C) transversal	%	1.1	0,9	0.8	0.5	0.6	0.4
Shrinkage at 200 °C longitudinal	%	2.6	2.6	3.2	1.2	1.2	0.8
Shrinkage at 200 °C transversal	%	3.8	3.3	3.2	1.3	1.8	1.0

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 08/22

Teonex® is a registered trademark of TOYOBO CO., Ltd.



Mechanical	Unit of measure					Test method
Nominal thickness	µm	100	125	188	250	JIS C2151
Tensile strength longitudinal	MPa	265	234	246	200	JIS C2318
Tensile strength transversal	MPa	264	257	244	210	JIS C2318
Elongation at break longitudinal	%	98	100	108	111	JIS C2318
Elongation at break transversal	%	100	117	109	143	JIS C2318
Shrinkage (30 min at 150 °C) longitudinal	%	0.6	-0.1	0.4	0.5	JIS C2318
Shrinkage (30 min at 150 °C) transversal	%	0.3	0.4	0.3	0.2	JIS C2318
Shrinkage at 200 °C longitudinal	%	1.0	-0.2	1,1	0.9	JIS C2318
Shrinkage at 200 °C transversal	%	1.0	0.8	0.7	0.4	JIS C2318

Electrical	Unit of measure	
Nominal thickness	µm	12
Dielectric strength	kV	-

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 08/22

Teonex® is a registered trademark of TOYOBO CO., Ltd.



Electrical	Unit of measure						
Nominal thickness	µm	16	25	38	50	75	100
Dielectric strength	kV	-	8	10	13	15	18

Electrical	Unit of measure				Test method
Nominal thickness	µm	125	188	250	JIS C2318
Dielectric strength	kV	20	25	29	JIS C2318

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 08/22

Teonex® is a registered trademark of TOYOBO CO., Ltd.

