

---

## Glass-fibre-duct-spacing-mats

Glass-fibre-profiles connected with insulating tapes.

---

### Attributes

Glass-fibre-duct-spacing-mats are a cost effective cooling channel solutions with free selectable / adjustable distances of single profiles. Also different profile-shapes can be used in one mat.

---

### Application

Glass-fibre-duct-spacing-mats are used in transformer and coils with cooling channels. They can be used in automated winding processes.

---

### Standards

Insulating material class H (180 °C)

---

### Delivery forms

Length: Up to 25 m

Width: Up to 3000 mm

Also deliverable in kits.

---

### Base

#### Profiles:

- dogbone
- square
- round

#### Insulating tapes:

- SynTherm® YT510
- NOMEX®
- SynTherm® DMD
- SynTherm® APA
- SynTherm® NPN
- MYLAR® A

Other materials on request.

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 05/18



General	Unit of measure	
Casting resin		Polyester / Epoxy
Reinforcement		Glas-Roving
Fibre content	%	> 60
Specific weight	g/cm <sup>3</sup>	> 1.85
Bending strength	N/mm <sup>2</sup>	480
Bending strength E-Module	N/mm <sup>2</sup>	35x10 <sup>3</sup>
Tensile strength	N/mm <sup>2</sup>	450
Compressive strength	N/mm <sup>2</sup>	240
Dielectric constant		apprx. 4
Specific resistance	Ωxcm	10 <sup>12</sup>
1-Min.-voltage test	kV/mm	8
Coefficient of expansion	K-1	10-15 <sup>-6</sup>
Water absorption	%	< 5
Thermal conductivity	W/m*K	0.3
Thermal class		H (180 °C)

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 05/18

