**Product datasheet** Intertape® 51597 Page 1 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| Intertape <sup>®</sup> | 51597 |  |  |  |
|------------------------|-------|--|--|--|
|                        |       |  |  |  |

Intertape $^{\circ}$  51597 is a glass filament reinforced polyester film with acrylic adhesive.

## **Standards**

UL-File-No.: E20780 CSA-File: LR94980

## **Delivery forms**

• Width: from 2.5 mm in 0.1 mm increments

Core diameter: 76 mm (3")Special widths on request

| Color       |  |  |  |  |  |
|-------------|--|--|--|--|--|
| Transparent |  |  |  |  |  |
|             |  |  |  |  |  |
| Glue        |  |  |  |  |  |
| Acrylate    |  |  |  |  |  |
|             |  |  |  |  |  |
| Adhesive    |  |  |  |  |  |
| One-sided   |  |  |  |  |  |

## **Storage**

Updated 07/20

12 months at room temperature. Adhesive tapes should be stored in a cool, dry place at approx. 20  $^{\circ}$ C and 50 - 60  $^{\circ}$ C relative humidity. The storage period should not exceed 12 months.







SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| General                                | Unit of measure |                                          |  |
|----------------------------------------|-----------------|------------------------------------------|--|
| Type/ Ordering information             |                 | Intertape® 51597                         |  |
| Standard colours                       |                 | Transparent                              |  |
| Backing                                |                 | Glass filament reinforced polyester film |  |
| Backing thickness                      | mm              | 0.140                                    |  |
| Adhesive                               |                 | Acrylate                                 |  |
| Dielectric constant (AC, 23 °C, 50 Hz) |                 | 1.82                                     |  |
| Elongation at break                    | %               | 5                                        |  |
| Electrolyt. corrosion value            |                 | 1.0 Direct/A, 1                          |  |
| Flammability class                     |                 | BU 2                                     |  |
| Thermal class                          |                 | 155 °C (F)                               |  |
| Total thickness                        | mm              | 0.165                                    |  |
| Dielectic strength                     | kV              | 5                                        |  |
| Tensile strength                       | N/cm            | 438                                      |  |
| Adhesiveness / Adhesion to steel       | N/cm            | 4.4                                      |  |
| Insulation resistance                  | ΜΩ              | 10^4                                     |  |





