**Product datasheet** Intertape® 54108 Page 1


SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



Intertape® 54108			
Intertape® 54108 consists of a polyester backing with a tightly cured rubber adhesive.			
Standards			
UL-File-Nr.: E20780			
Delivery forms			
Width: from 2.5 mm in 0.1 mm increments			
• Core diameter: 76 mm (3")			
Special widths on request			
Color			
Cream			
Glue			
Rubber			
Adhesive			
One-sided			
Storage			

12 months at room temperature. Adhesive tapes should be stored in a cool, dry place at approx. 20 °C and 50 - 60 % relative humidity. The storage period should not exceed 12 months.





Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data

SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



General	Unit of measure	
Type/ Ordering information		Intertape® 54108
Standard colours		cream
Backing		polyester film
Backing thickness	mm	0.025
Adhesive		rubber
Total thickness	mm	0.061
Electrolyt. corrosion value		1.0 Direct/A, 1
Flammability class		BU 1
Thermal class		130 °C (B)
Dielectic strength	kV	5
Tensile strength	N/cm	44
Adhesiveness / Adhesion to steel	N/cm	5.5
Elongation at break	%	100
Insulation resistance	ΜΩ	10^6





