Product datasheet Intertape® 51597 Page 1 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



Into	rta	no®	51	597

Intertape® 51597 is a glass filament reinforced polyester film with acrylic adhesive.

Standards

UL-File-No.: E20780 CSA-File: LR94980

Delivery forms

• Width: from 2.5 mm in 0.1 mm increments

Core diameter: 76 mm (3")Special widths on request

Storage

12 months at room temperature. Adhesive tapes should be stored in a cool, dry place at approx. 20 $^{\circ}$ C and 50 - 60 $^{\circ}$ C relative humidity. The storage period should not exceed 12 months.







SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



General	Unit of measure		
Type/ Ordering information		Intertape® 51597	
Standard colours		Transparent	
Backing		Glass filament reinforced polyester film	
Backing thickness	mm	0.140	
Adhesive		Acrylate	
Dielectric constant (AC, 23 °C, 50 Hz)		1.82	
Elongation at break	%	5	
Electrolyt. corrosion value		1.0 Direct/A, 1	
Flammability class		BU 2	
Thermal class		155 °C (F)	
Total thickness	mm	0.165	
Dielectic strength	kV	5	
Tensile strength	N/cm	438	
Adhesiveness / Adhesion to steel	N/cm	4.4	
Insulation resistance	ΜΩ	10^4	

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 05/24





