SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



SynTherm® AP/80

SynTherm® AP/80 is a flexible 2-layer insulation made of polyester film with calandered aramid paper overlay.

Attributes

The proven dielectric properties of the polyester film and the excellent mechanical and thermal properties of the outer aramid paper layers result in a high performance insulating material. The ability of the outer layers to absorb impregnants results in exceptional bonding between all winding components.

Application

SynTherm® AP/80 is a cost-effective insulating material used in electric motors as slot insulation, phase insulation and wedges.

SynTherm® AP/80 is used as core, interlayer und final insulation for transformers.

Standards

- Suitable for class F (155 °C) systems.
- UL approved e.g. E247773

Delivery forms

Total thickness in μm : 270 Other thicknesses on request

SynTherm® AP/80 is available:

in tapes: depending on material thickness on request beginning at 6mm (thin material)

• in rolls: 968 mm

Feathering:

- Depth approx. 1 12 mm; distance approx. 1 10 mm
- From widths of 10 mm to 240 mm, thickness on request

Base

PET-film + aramid paper







SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



Typical mechanical properties	Unit of measure	Values
Nominal thickness	mm	0.27
Typical thickness	mm	0.27±15 %
Film thickness	μm	190
Aramid paper thickness	μm	80
Specific weight	g/m²	335
Tensile strength longitudinal	N/cm	280
Tensile strength transversal	N/cm	330

Typical electrical properties	Unit of measure	Values
Nominal thickness	mm	0.27
Dielectric strength	kV	24





