
SynTherm® NPN/50

SynTherm® NPN/50 is a flexible 3-ply insulation consisting of a polyester film with a calandered Nomex® layer with yellow strips.

Attributes

The proven dielectric properties of the polyester film and the excellent mechanical and thermal properties of the outer Nomex® layers result in a high performance insulating material. The ability of the outer layers to absorb impregnants results in exceptional bonding between all winding components.

Application

SynTherm® NPN/50 is a cost-effective insulating material which can be installed in suitable insulating systems of class H (180 °C) and is used in electric motors as slot insulation, phase insulation and wedges. SynTherm® NPN/50 is used as core, interlayer und final insulation for transformers.

Standards

- Suitable for class H (180 °C) systems
- Insulating material according to IEC 60626
- UL approved, e.g. E247773
- RoHS compliant acc. to 2011/65/EU
- Test standard IEC 60626-2
- Sample conditioning acc. to standard atmosphere 23/50

Delivery forms

Total thickness in µm:

130, 160, 180, 220, 240, 310, 370, 410, 470

SynTherm® NPN/50 can be supplied:

- in slit rolls from widths of 6 mm (depending on thickness) and above
- in rolls approx. width of 900 mm
- in sheets on request: approx. 600 x 900 mm or 900 x 1000 mm

Optional overall diameter of the slit rolls/ rolls

approx. 240, 330 or 450 mm.

Feathering:

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 10/18

Nomex®, Kapton®, KAPTON® are registered trademarks of E.I. Du Pont de Nemours and Company.
SynTherm® is a registered trademark of SynFlex.



-
- depth approx. 1 - 12 mm, distance approx. 1 - 10 mm
 - from widths of 10 to 240 mm and thickness of 0.24 mm
-

Base

PET-film + calandered Nomex® on both sides

Mechanical	Unit of measure						
Total thickness	mm	0.13	0.16	0.18	0.22	0.24	0.31
Thickness tolerance max.	%	± 15	± 15	± 15	± 15	± 15	± 15
Film thickness	µm	23	50	75	100	125	190
Nomex® paper thickness	µm	50	50	50	50	50	50
Specific weight	g/m ²	135	170	200	230	270	360
Tensile strength longitudinal*	N/mm ²	90	95	95	100	100	100
Tensile strength transversal*	N/mm ²	60	80	90	90	90	100
Elongation at break longitudinal*	%	15	15	20	20	20	25
Elongation at break transversal*	%	20	30	40	40	40	50

Mechanical	Unit of measure			
Total thickness	mm	0.37	0.41	0.47
Thickness tolerance max.	%	± 10	± 10	± 10

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 10/18

Nomex®, Kapton®, KAPTON® are registered trademarks of E.I. Du Pont de Nemours and Company.
SynTherm® is a registered trademark of SynFlex.



Mechanical	Unit of measure			
Film thickness	µm	250	300	350
Nomex® paper thickness	µm	50	50	50
Specific weight	g/m ²	450	520	590
Tensile strength longitudinal*	N/mm ²	100	100	100
Tensile strength transversal*	N/mm ²	100	100	100
Elongation at break longitudinal*	%	25	25	25
Elongation at break transversal*	%	50	50	35

Electrical	Unit of measure						
Total thickness	µm	0.13	0.16	0.18	0.22	0.24	0.31
Dielectric strength*	kV	8	10	12	15	18	20

Electrical	Unit of measure			
Total thickness	µm	0.37	0.41	0.47
Dielectric strength*	kV	26	27	29

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 10/18

Nomex®, Kapton®, KAPTON® are registered trademarks of E.I. Du Pont de Nemours and Company.
SynTherm® is a registered trademark of SynFlex.

