SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



## Glass-fibre-duct-spacing-mats

Glass-fibre-profiles connected with insulating tapes.

### **Attributes**

Glass-fibre-duct-spacing-mats are a cost effective cooling channel solutions with free selectable / adjustable distances of single profiles. Also different profile-shapes can be used in one mat.

## **Application**

Glass-fibre-duct-spacing-mats are used in transformer and coils with cooling channels. They can be used in automated winding processes.

#### **Standards**

Insulating material class H (180 °C)

### **Delivery forms**

Length: Up to 25 m Width: Up to 3000 mm Also deliverable in kits.

#### **Base**

### **Profiles:**

- dogbone
- square
- round

# **Insulating tapes:**

- SynTherm® YT510
- NOMEX®
- SynTherm® DMD
- SynTherm® APA
- SynTherm® NPN
- MYLAR® A

Other materials on request.

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data

Updated 05/18

Nomex® is a registered trademark of E.I. Du Pont de Nemours and Company. SynTherm® is a registered trademark of SynFlex

Mylar®, Melinex®are registered trademarks of Mylar Specialty Films U.S. Limited Partnership.







SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



General	Unit of measure	
Casting resin		Polyester / Epoxy
Reinforcement		Glas-Roving
Fibre content	%	> 60
Specific weight	g/cm³	> 1.85
Bending strength	N/mm²	480
Bending strength E-Module	N/mm²	35x10^3
Tensile strength	N/mm²	450
Compressive strength	N/mm²	240
Dielectric constant		apprx. 4
Specific resistance	Ωxcm	10^12
СТІ		KC 600
1-Minvoltage test	kV/mm	8
Coefficient of expansion	K-1	10-15^-6
Water absorption	%	< 5
Thermal conductivity	W/m*K	0.3
Thermal class		H (180 °C)

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.









