Product datasheet 3M[™] no. 1350F-2 Page 1 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



3M[™] no. 1350F-2

3M electro-insulating tape 1350F-2 is a polyester adhesive tape with pressure sensitive acrylate adhesive.

Attributes

The printable $3M^{\infty}$ electro-insulating tape no. 1350F-2 is characterised by its high initial adhesiveness and tear resistance as well

as its good resistance to solvents and chemicals. The tape is flame retardant according to UL 510 and is UL-approved up to 130 °C.

Application

As top and interlayer insulation, final insulation, taping and insulation of coils and wires. The tape is characterised by its extensive range of

applications, it is UL approved and included in numerous UL systems.

Delivery forms

• Width: from 2.5 mm, in 0.1 mm increments

Standard length: 66 mCore diameter: 76 mm (3")Special widths on request

| \sim 1 | I | _ |
|----------|---|---|
| (7 | ш | ρ |
| | | |

Acrylate

Adhesive

one-sided

Storage

Adhesive tapes should be stored in a cool, dry place at approx. 15-25 °C and 65 % relative humidity. Special for 1350F-2 of 3M⁻⁻ is the storage period of 5 years.





SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| General | Unit of measure | |
|----------------------------------|-----------------|-------------------------------------|
| Flame retardant | | According to UL 510 |
| UL FILE NO. | | E17385 OANZ 2 |
| Thermal class | | 130 °C (B) |
| Electrolyt. corrosion value | | 1.0 |
| Dielectic strength | kV | 7 |
| Adhesiveness / Adhesion to steel | N/cm | 3.3 |
| Elongation at break | % | 110 |
| Tensile strength | N/cm | 88 |
| Total thickness | mm | 0.083 |
| Adhesive | | Acrylate |
| Backing thickness | mm | 0.05 |
| Backing | | Polyester |
| Type/ Ordering information | | 1350F-2 by 3M™ |
| Standard colours | | yellow (1350FY-2), white (1350FW-2) |





