
Damisol® 3500 LoV 1-component-resin

Damisol® 3500 LoV is a Freon resistant heat curing epoxy resin with low viscosity.

Attributes

Damisol® 3500 LoV has the following properties:

- low viscosity
- Freon resistant
- very low VOC emission
- suitable for dipping- and vacuum-impregnating processes
- excellent long-term heat resistance

Application

Damisol® 3500 LoV is mainly used for the impregnation of medium and low voltage industrial motors. Due to the very good electrical, mechanical and thermal properties of Damisol® 3500 LoV it is also suitable for traction motors and transformers.

Standards

- Thermal class H (UL 1446)

Delivery forms

Damisol® 3500 LoV is available in:

- 25 kg cans
- 200 kg drums
- 1000 kg container

Storage

Damisol® 3500 LoV can be stored 12 months in sealed containers at room temperature (max. 25 °C). Higher temperature can be reached during short period of time. If storing the resin in a supply tank, dry air or "Nitrogen" is recommended.

Hardening

The curing time is between 5 h at 160 °C and 2 h at 170 °C. The exact curing time depends on different parameters.

Protection

Please avoid contact of Damisol® 3500 LoV with skin. Use safety gloves and glasses.

Please refer to the material safety data sheet for complete information.

Processing

The most frequent processes are atmospheric dipping as well as VPI.

Mechanical	Unit of measure	Condition	Values	Test method
Gel time	min	at 130 °C	12±3	gel norm 20g
Glass transition temperature	°C		122 °C	IEC 61006
Water absorption	%	after 24h at 23 °C	≤ 0.3	ISO 62 (method 1)
Bond strength	daN	at 180 °C	8.3	IEC 1033

Chemical	Unit of measure	Condition	Values	test method
Resistance	%	transformer oil	< 0.1	ISO 175
Resistance	%	chemicals HCl 10 %	≤ 0.14	ISO 175

Liquid phase	Unit of measure	Condition	Values	test method
Colour			yellowish	
Flashpoint	°C		≥100	
Viscosity	mPas	at 25 °C	600 ± 200	Brookfield
VOC acc. 31. BlmSchV	%		< 2	IEC 60455-3

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 06/21



Product datasheetDamisol® 3500 LoV 1-component-resin
Page 4SynFlex Elektro GmbH
Auf den Kreuzen 24
D-32825 Blomberg Germany
Telefon +49-5235-968-0
E-Mail info@synflex.de

Electrical	Unit of measure	Condition	Values	Test method
Dielectric strength at 23 °C and 50 % r.h.	kV/mm		159	DIN 46448/VDE 0360
Dielectric strength at 23 °C after 96 h storage at 92 % r.h.	kV/mm		143	DIN 46448/VDE 0360
Dielectric loss factor	%	at 25 °C tan delta	< 1	IEC 60250
Dielectric loss factor	%	at 105 °C tan delta	≤ 2	IEC 60250
Dielectric loss factor	%	130 °C tan delta	≤ 5.5	IEC 60250

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 06/21

