
Voltatex® 4100 1-component-resin

Voltatex® 4100 is a clear, ready-to-use impregnating resin, thermosetting, yellow-brown glazing, styrene-free 1K dip resin based on unsaturated polyesterimide resins.

Attributes

- single component
- very high capillary activity
- low evaporation losses while processing
- high resin retention in the object
- low draining losses in the oven
- high efficiency due to favourable curing conditions and
- excellent impregnating results

The cured resin compound is characterized by:

- good resistance against solvent gases and against long term thermal stress
- high bond strength
- low tendency to crack
- tough-elastic compound

Application

- electric motors
- transformers
- suitable for: Insulation systems of thermal class 180 (H)

Standards

Suitable for: Insulating systems up to thermal class H acc. to IEC 60085

- Temperature index according to IEC 60455-3-5: Type 180
- UL file no.: E 101752 (M) Underwriters Laboratories Inc, USA.
- RoHS-compliant 2011/65/EC
- REACH-compliant 2006/121/EU
- Polybrominated Diphenylether 2003/11/EU
- UL approved with enamelled Cu wire:

Twisted Pair ASTM D2307 MW 30:200

MW 35:180

Helical Coil ASTM D2519 MW 30:200

Electro insulating systems according to UL 1446 (IEC 61858)

Class 130 C190HE

R150HE

Z130HE

Z150HE

Class 155 C290HE

CZ255HE

R201HE

R203HE

Z200HE

Delivery forms

Voltatex® 4100 is supplied in one-way-cans containing 25 kg.

Storage

In closed original cans the resin can be stored for more than 6 months if provided storage temperature does not exceed 25 °C. Opened containers have to be closed immediately to protect the material from daylight!

Hardening

In order to minimize evaporation of reactive components while curing the impregnated objects should be heated up to the curing temperature in the shortest possible time. The air flow in the curing oven should be kept to the minimum permitted by safety considerations.

Curing time: at 130 °C - 2h

Protection

Cured Voltatex® 4100 is biologically inactive and not dangerous to health. When processing the liquid resin please refer to the Material Safety Data Sheet (MSDS) for Voltatex® 4100.

Processing

The impregnating resin can be applied by using

- all kind of conventional dip & bake equipment
- continuous and vacuum dip processes
- VPI process

Unlimited tank stability can be achieved as long as Voltatex® 4100 is kept below 25 °C and at least 30 % of the tank content is used and replaced

with fresh resin per month.

Cleaning

Once cured Voltatex® 4100 is almost insoluble. Therefore, application equipment should be cleaned regularly with cleaner Voltatex® T050.

All equipment cleaning and maintenance should be carried out in accordance with the equipment manufacturer's instructions.

Mechanical	Unit of measure	Conditions	Values	Test method
Bond strength of twisted pairs 25 °C	N		120 ± 10	IEC 60455-2, test method A acc. IEC 61033
Bond strength of twisted coils 130 °C	N		28 ± 5	IEC 60455-2, test method A acc. IEC 61033
Bond strength of twisted coils 155 °C	N		27 ± 4	IEC 60455-2, test method A acc. IEC 61033
Bond strength of twisted coils 180 °C	N		26 ± 4	IEC 60455-2, test method A acc. IEC 61033
Shore-D-hardness		25°C	60 ± 5	IEC 60455-2, test method acc. ISO 868
Bond strength IEC 60317-13	°C	MW 35	209	IEC 61033, method B, final point 22 N

Thermal	Unit of measure	Conditions	Values	Test method
Temperature index	°C		180	IEC 60455-3-5, test method acc. IEC 60216
Testing voltage IEC 60317-8	°C	MW 30	207	IEC 60172
Testing voltage IEC 60317-13	°C	MW 35	196	IEC 60172

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 02/19

Voltatex® is a registered trademark of Axalta Coating Systems LLC., Philadelphia PA 19103, USA.



Thermal	Unit of measure	Conditions	Values	Test method
Glass transition temperature	°C		ca. 10-60	
Heat conductivity	W(m*k)^-1		0.17	acc. DIN 51046

Chemical	Unit of measure	Conditions	Values	Test method
Resistance		Transformatoröl	resistant	IEC 60455-2, test method acc. ISO 175
Water absorption	%	after 96h at 23 °C	0.6-0.8	IEC 60455-2, test method 1 acc. ISO 62

Liquid phase	Unit of measure	Values	Test method
Viscosity	mPas	250 ± 30	at 25 °C acc. DIN 53019
VOC acc. 31. BLMschV		appr. 5.7 %	acc. DIN EN 60455-3-5:2006
Flow time	s	65 ± 8	at 23 °C acc. DIN 53211
Reaction process gel time	min	6.0-12.0	at 100 °C acc. company standard
Reaction process reaction time	min	14.0-24.0	at 100 °C acc. company standard

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 02/19

Voltatex® is a registered trademark of Axalta Coating Systems LLC., Philadelphia PA 19103, USA.



Electrical	Unit of measure	Conditions	Typ. values	Test method
Dielectric strength at 23 °C and 50 % r.h.	kV/mm		60	IEC 60455-2, test method acc. IEC 60243-1
Dielectric strength at 155 °C	kV/mm		70	IEC 60455-2, test method acc. IEC 60243-1
Dielectric strength at 23 °C after 96 h storage at 92 % r.h.	kV/mm		65	IEC 60455-2, test method ac. IEC 60243-1
Dielectric strength at 105 °C after 168 h oil immersion	kV/mm		94	IEC 60455-2, test method acc. IEC 60243-1
Specific volume resistance at 155 °C	Ω*cm		10 ⁹ - 10 ¹¹	acc. IEC 60455-2, test method acc. IEC 60093
Creep resistance			CTI 600 M	acc. IEC 60455-2, test method acc. 6.2 IEC 60112
Loss factor cross section 0.2=200x10 ⁻³	°C		110-150	IEC 60455-2, test method acc. IEC 60250

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 02/19

Voltatex® is a registered trademark of Axalta Coating Systems Llc., Philadelphia PA 19103, USA.

