

Teonex[®] Q5100

Teonex[®] Q5100 is a flexible, slightly cloudy, biaxially oriented polyethylenenaphthalate (PEN) film.

Attributes

Compared to PET polyester film, Teonex® Q5100 has optimum properties in every respect. The increased temperature resistance results in film approval in thermal class F (155 °C). It has a electrical relative

temperature index (RTI) of 180 °C and a mechanical RTI of 160 °C according to UL.

Further advantages of Teonex® Q5100 are:

- extremely high dielectric strength
- very good mechanical strength
- high-level of stiffnes
- low water absorption
- easy to laminate

Application

Teonex® Q5100 was specially developed for use in electric motors with increased load as slot insulation, phase insulation and wedges.

Standards

- Class F (155 °C) insulating material
- UL approved, file no. E51743

Delivery forms

Film thicknesses in µm:

• from 12, 16, 25, 38, 50, 75,100, 125, 188, 250

Teonex® Q5100 can be supplied:

- in slit rolls from widths of 6 mm (depending on thickness) and above.
- in rolls up to a width of 1,000 mm

Overall diameter of the slit rolls/ rolls

• approx. 240, 330 or 450 mm.

 $\ensuremath{\mathsf{Teonex}}\xspace{1.5mu}{\mathbb{R}}$ is a registered trademark of TOYOBO CO., Ltd.





Feathering:

- depth approx. 1 12 mm, distance approx. 1 10 mm
- from widths of 10 to 240 mm and thickness of 0.125 mm

Base

Polyethylennaphthalte

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 06/24

 ${\tt Teonex} \circledast$ is a registered trademark of TOYOBO CO., Ltd.





Mechanical	Unit of measure						
Nominal thickness	μm	12	16	25	38	50	75
Tensile strength longitudinal	МРа	300	330	340	320	290	290
Tensile strength transversal	МРа	330	340	350	320	300	280
Elongation at break longitudinal	%	100	90	100	110	120	100
Elongation at break transversal	%	90	80	90	110	120	100
Shrinkage (30 min at 150 °C) longitudinal	%	0.7	1.0	1.0	0.5	0,4	0.5
Shrinkage (30 min at 150 °C) transversal	%	0.3	0,3	0.4	0.3	0.3	0.4
Shrinkage at 200 °C Iongitudinal	%	2.6	2.7	2.7	1.2	0.8	1.0
Shrinkage at 200 °C transversal	%	3.5	1.7	1.9	1.3	0.8	1.0

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 06/24

 $\ensuremath{\mathsf{Teonex}}\xspace$ is a registered trademark of TOYOBO CO., Ltd.





Mechanical	Unit of measure					Test method
Nominal thickness	μm	100	125	188	250	
Tensile strength longitudinal	МРа	260	260	250	210	JIS C2318
Tensile strength transversal	МРа	280	260	240	190	JIS C2318
Elongation at break longitudinal	%	110	100	110	120	JIS C2318
Elongation at break transversal	%	100	100	100	110	JIS C2318
Shrinkage (30 min at 150 °C) longitudinal	%	0.3	0,2	0.2	0.2	JIS C2318
Shrinkage (30 min at 150 °C) transversal	%	0.4	0.3	0.4	0.3	JIS C2318
Shrinkage at 200 °C longitudinal	%	0.9	1.0	1,1	0.9	JIS C2318
Shrinkage at 200 °C transversal	%	1.1	0.8	0.7	0.7	JIS C2318

Electrical	Unit of measure	
Nominal thickness	μm	12
Dielectic strength	kV	9.6

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 06/24

Teonex® is a registered trademark of TOYOBO CO., Ltd.





Electrical	Unit of measure						
Nominal thickness	μm	16	25	38	50	75	100
Dielectic strength	kV	9.6	8.1	11.2	12.7	16.2	18.0

Electrical	Unit of measure				Test method
Nominal thickness	μm	125	188	250	
Dielectic strength	kV	20.7	25.0	28.7	

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 06/24

 ${\tt Teonex} \circledast$ is a registered trademark of TOYOBO CO., Ltd.

