SynFlex Elektro GmbH
Auf den Kreuzen 24
D-32825 Blomberg Germany
Telefon +49-5235-968-0
E-Mail info@synflex.de

SynTherm® H (Polyimide film)

SynTherm® H is a polyimide film manufactured with the raw materials of pyromellitic dianhydride and 4.4-diaminodiphenyl ether synthetic resin.

Attributes

SynTherm® H offers a unique combination of properties at the highest level, which are recommended for many applications in numerous branches. SynTherm® H sustains it's excellent physical, electrical and mechanical properties within a wide temperature range. For short time it is also applicable for temperatures from -269 °C to +400 °C and it is used in systems of class H. It has low flamability, is self-extinguishing and has no melting point. SynTherm® H offers a high chemical resistance - an organic solvent is unknown up to now. It has also a high resistance to beta and gamma radiation.

Application

SynTherm® H is especially for applications with high operating temperatures for which other films are not applicable.

Standards

- UL listed(E358562), UL 94 V-0, UL RTI >200 °C

Delivery forms

Film thickness in µm:

25, 50, 75, 100, 125, 150, 175, 200

SynTherm® H can be supplied:

- in slit rolls from widths of 6 mm (depending on thickness)
- in rolls approx. width 500 mm up to 1000 mm

Feathering:

- depth approx. 1 - 12 mm, distance approx. 1 - 10 mm
- from widths of 10 to 240 mm and thickness on request

Base

Pyromellitic dianhydride and 4.4-diaminodiphenyl ether synthetic resin

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 07/21

SynTherm® is a registered trademark of SynFlex.

SynFlex Elektro GmbH
Auf den Kreuzen 24
D-32825 Blomberg Germany
Telefon +49-5235-968-0
E-Mail info@synflex.de

Typical mechanical properties	Unit of measure						
Nominal thickness	µm	12.5	25	40	50	75	100
Thickness tolerance	µm	+1.5/-2.5	+4/-3	+6/-5	+7/-6	+8/-6	+8/-7
Density	g/cm³	1.42	1.42	1.42	1.42	1.42	1.42
Shrinkage at 150 °C	%	1.0	1.0	1.0	1.0	1.0	1.0
Tensile strength longitudinal	MPa	135	135	135	135	135	135
Tensile strength transversal	MPa	115	115	115	115	50	115
Elongation at break longitudinal	%	50	35	35	50	50	50
Elongation at break transversal	%	50	35	35	50	50	50

Typical mechanical properties	Unit of measure				
Nominal thickness	µm	125	150	175	200
Thickness tolerance	µm	±8	±8	±8	±8
Density	g/cm³	1.42	1.42	1.42	1.42

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 07/21

SynTherm® is a registered trademark of SynFlex.

SynFlex Elektro GmbH
Auf den Kreuzen 24
D-32825 Blomberg Germany
Telefon +49-5235-968-0
E-Mail info@synflex.de

Typical mechanical properties	Unit of measure				
Shrinkage at 150 °C	%	1.0	1.0	1.0	1.0
Tensile strength longitudinal	MPa	135	135	135	135
Tensile strength transversal	MPa	115	115	115	115
Elongation at break longitudinal	%	50	60	50	50
Elongation at break transversal	%	50	60	50	50

Typical electrical properties	Unit of measure						
Nominal thickness	µm	12.5	25	40	50	75	100
Dielectric strength short term AC	kV/mm	130	150	130	110	100	100
Specific surface resistivity	Ω/m	1x10^13	1x10^13	1x10^13	1x10^13	1x10^13	1x10^13
Volume resistivity	Ω.m	1x10^10	1x10^10	1x10^10	1x10^10	1x10^10	
Dielectric constant (AC 50 Hz, 25 °C)		3.5±0.4	3.5±0.4	3.5±0.4	3.5±0.4	3.5±0.4	3.5±0.4
Dielectric loss factor (AC 50 Hz, 25 °C)		4.0 x 10^-3	4.0x10^-3	4.0x10^-3	4.0x10^-3	4.0x10^-3	4.0x10^-3

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 07/21

SynTherm® is a registered trademark of SynFlex.

SynFlex Elektro GmbH
Auf den Kreuzen 24
D-32825 Blomberg Germany
Telefon +49-5235-968-0
E-Mail info@synflex.de

Typical electrical properties	Unit of measure						
Specific surface resistivity	Ω/m	1x10^10					

Typical electrical properties	Unit of measure				
Nominal thickness	µm	125	150	175	200
Dielectric strength short term AC	kV/mm	100	120	100	100
Specific surface resistivity	Ω/m	1x10^13	1x10^13	1x10^13	1x10^13
Volume resistivity	Ω.m	1x10^10	1x10^10	1x10^10	1x10^10
Dielectric constant (AC 50 Hz, 25 °C)		3.5±0.4	3.5±0.4	3.5±0.4	3.5±0.4
Dielectric loss factor (AC 50 Hz, 25 °C)		4.0x10^-3	4.0x10^-3	4.0x10^-3	4.0x10^-3

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 07/21

SynTherm® is a registered trademark of SynFlex.