
SHTherm® 210 Flat

- Enamelled flat copper wire, thermoresistant
- Polyesterimide overcoated with
- polyamide-imide enamel
- Class 200/220

Attributes

SHTherm® 210 Flat is a highly thermoresistant rectangular enamelled copper wire of heat performance class N with a wide range of excellent quality features. Its insulation film consists of 2 different coatings on top of one another. These ensure a very good permanent thermal and overload resistance, excellent resistance against mechanical stress, as well as an excellent resistance to chemical attacks of commercial washing and cleaning agents, impregnating varnishes and resins, sealing compounds, thinners, solvents and refrigerants, oils as well as their vapours. This range of excellent features make SHTherm® 210 Flat an all-round wire meeting the requirements of all applications with above average requirements to processing and operational features or operational safety in electrical systems.

The consistent further developments carried out by our R&D team allow this excellent “all-round” wire to be optimised to take into account specific customer requirements (e.g. improved adhesion after ageing, workability, electrical characteristics).

Application

E-mobility, electric motors, generators, transformers, hybrid constructions

Standards

IEC / DIN EN 60317-29

NEMA MW 36-C/ MW 38-C

UL approved

Delivery forms

Grade 1: on request

Grade 2:

width: 2.000 - 20.000 mm

thickness: 0.800 - 5.000 mm

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 05/18



Typical properties of enamelled flat copper wire 5.60 x 3.55 mm, with insulation film grade 2

Mechanical	Unit of measure	Set value	Actual value
Bare wire width	mm	5.550-5.650	as set value
Width with varnish	mm	5.67 - 5.82	as set value
Bare wire thickness	mm	3.500-3.600	as set value
Thickness with varnish	mm	3.62 - 3.77	as set value
Varnish increase	µm	120 - 170	as set value
Elongation and adhesion		mandrel diameter	
Elongation and adhesion (no cracks in varnish after winding) - bend over width		4 x width	3 x width
Elongation and adhesion (no cracks in varnish after winding) - bend over thickness		4 x thickness	3 x thickness
Elongation and adhesion (no cracks in varnish after winding) - elongation		15 % with cracks < 1 x width	32 % without cracks
Pencil hardness of varnish		H	4H - 5H
Elongation at break	%	≥ 32	≥ 38

Thermal	Unit of measure	Set value	Actual value
Temperature index	°C	200/220	210/220

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 05/18



Thermal	Unit of measure	Set value	Actual value
Heat shock at 220 °C (no cracks in varnish coat after winding)		mandrel diameter: 6 x thickness	mandrel diameter: 4 x thickness
Solderability		no	no

Electrical	Unit of measure	Set value	Actual value
Dielectric strength RT	kV	≥ 2.0 (ball pit)	≥ 3 (ball pit)
High voltage discontinuities 750V		/	≤ 7 on 100 m
Electrical conductivity of Cu conductor	MS/m	58 - 59	≥ 58.5

Chemical	Set value	Actual value
Pencil hardness (storage in standard solvent ½ h / 60 °C)	min. H	3H - 5H
Pencil hardness (storage in alcohol ½ h / 60 °C)	min. H	3H - 5H
Resistance to commercial impregnants^(1)	/	yes
Resistance to commercial refrigerants (1)	/	yes
Resistance to dry transformer oils (1)	/	yes
Resistance to hydraulic oils (1)	/	yes

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 05/18



(1) Due to the variety of individual applications we cannot make any generally binding commitments regarding the compatibility. We recommend testing compatibility with the materials being used.

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 05/18

