
Kaladex® 2000 PEN film

Kaladex® 2000 is a biaxially oriented polyethylene naphthalate (PEN) film. PEN is a high-performance polyester offering improved mechanical, thermal and chemical properties compared with conventional polyethylene terephthalate (PET) films, while maintaining good processing characteristics.

Attributes

Kaladex® 2000 combines high mechanical strength with excellent heat and hydrolysis resistance, good dimensional stability and low oligomer extraction. This balanced property profile makes the film suitable for applications with demanding thermal, mechanical and electrical requirements.

Application

Kaladex® 2000 is used in a wide range of electrical and electronic applications, including insulation for motors and transformers, capacitors, flexible printed circuits and fuel cells. PEN is particularly suitable for applications where conventional PET films reach their performance limits, but the full performance capabilities of polyimide (PI) films are not necessary. This makes PEN a cost-effective material solution for applications requiring a higher performance level than PET without the need for PI.

Standards

- Class F (155 °C) insulating material
- UL listed, File No. E93687
- RoHS compliant according to 2011/65/EU

Delivery forms

Total thickness in µm:

- 25, 38, 50, 75, 100

Kaladex® 2000 is available:

- in tapes from 6 mm width
- in rolls approx. 1,000 mm wide

Base

Polyethylene naphthalate (PEN)

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 09/26



Mechanical	Unit of measure					
Nominal thickness	µm	25	38	50	75	100
F5-value longitudinal (MD)	kg/mm ²	15	15	15	15	15
F5-value, transversal (CMD)	kg/mm ²	16	16	16	16	16
Tensile strength longitudinal (MD)	kg/mm ²	25	25	25	25	25
Tensile strength transversal (CMD)	kg/mm ²	28	28	28	28	
Elongation at break longitudinal *	%	90	90	90	90	90
Elongation at break transversal *	%	65	65	65	65	65
Density	g/cm ²	1.36	1.36	1.36	1.36	1.36

Optical	Unit of measure	
Nominal thickness	µm	25
Haze	%	6

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 09/26



Optical	Unit of measure				
Nominal thickness	µm	38	50	75	100
Haze	%	8	13	18	25

Thermal	Unit of measure					
Nominal thickness	µm	25	38	50	75	100
Fusion temperature	°C	269	269	269	269	269
Glass transition temperature	°C	121	121	121	121	121
Shrinkage longitudinal (MD) / 190 °C, 5 min	%	1.2	1.2	1.2	1.2	1.2
Shrinkage transversal (CMD) / 190 °C, 5 min	%	1.4	1.4	1.4	1.4	1.4
Shrinkage longitudinal (MD) / 150 °C, 30 min.	%	0.6	0.6	0.6	0.6	0.6
Shrinkage transversal (CMD) / 150 °C, 3 min.	%	0.6	0.6	0.6	0.6	0.6
Coefficient of thermal expansion longitudinal (MD)	10 ⁻⁶ /°C	13	13	13	13	13
Coefficient of thermal expansion transversal (CMD)	10 ⁻⁶ /°C	13	13	13	13	13

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 09/26



Thermal	Unit of measure					
Hygroscopic expansion coefficient longitudinal (MD)	10 ⁻⁶ /%RH	11	11	11	11	11
Hygroscopic expansion coefficient transversal (CMD)	10 ⁻⁶ /%RH	11	11	11	11	11
Mechanical RTI	°C	160	160	160	160	160
Electrical RTI	°C	180	180	180	180	180

Electrical	Unit of measure	
Nominal thickness	µm	25
Dielectric strength	kV/mm	331

Electrical	Unit of measure				
Nominal thickness	µm	38	50	75	100
Dielectric strength	kV/mm	261	248	198	187

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 09/26

